



Whatever  
May Come.



Ultimate High Traffic Performance

Bona Traffic HD



# Ultimate High Traffic Performance

## Bona Traffic HD

Bona sets the standards again, now introducing a new 2-component polyurethane finish to meet the ultimate demands of wooden floors exposed to extreme wear. Taking performance even further, significantly greater scratch, scuff and chemical resistance is quickly achieved only 24 hours after application.

With 40% less VOC compared to the classic Bona Traffic finish, Bona Traffic HD reflects Bona's long-term commitment of working towards more sustainable products. Setting a new definition of ultimate performance finish for professional contractors, Bona Traffic HD is the finish for the future.



### Application

Designed to last, Bona Traffic HD ensures ultimate durability for extremely high-traffic areas.

- Heavy-traffic floors: airports, hotels, shopping malls etc.

### Key Benefits

- Ultimate durability
- Early performance development – ready to use 24 hours after coating
- Low VOC < 5%
- Extremely low odour
- Non-yellowing surface
- DIBt approved
- Excellent absorption of floor unevenness
- Improves adhesion of over lacquer

### Gain for the contractor

- Faster curing saves valuable time for both contractors and floor owners
- Improved working conditions

### Technical Data

Type of varnish:	2-component waterborne polyurethane topcoat
Solids content:	~32%
VOC:	max 52g/litre (incl. hardener)
Resistance to wear:	1-2 mg/100 revolutions (SIS 923509)
Sheen (at 60°):	Silkmatt 40-45%, Matt 20-25%, Extra Matt ~10%
Mixing ratio:	1 part Bona Traffic HD Hardener to 10 parts Bona Traffic HD
Pot life:	4 hours at 20°C (shorter if warmer)
Dilution:	If required, dilute with 4% Bona Retarder for a longer open time
Drying time, until sanding/recoating:	- Ready in 2-3 hours* - Full use: 24 hours* - Full hardness: 5 days* <i>*under normal climate conditions, 20°C/60% R.H.</i>
Application rate:	8-10 m <sup>2</sup> /litre (120-100g/m <sup>2</sup> ) per coat
Safety:	Varnish: Unclassified Hardener: Classified (see Safety Data Sheet)
Cleaning:	Clean with water. Dried material can be removed with acetone.
Shelf life:	1 year from date of production in unopened original container
Storage/transport:	The temperature must not fall below +5°C or exceed +25°C during storage and transport.
Pack size:	3 x 4.95 litres incl. hardener