

## BONA TRAFFIC Sitework

## Surface preparation

The surface which is to be coated must be well sanded, dry and free from sanding dust, oil, wax and other contamination. The Bona Scrad system, sanding disc/screen or sandpaper grade no. 120 or finer should be used for the final sanding of the wood. The best results are obtained using a buffing machine.

## Preparation of factory pre-finished and previously finished floors

General conditions for an overcoating to be possible are:

- 1. The surface which is to be coated must be completely clean. Floors which have been previously treated with wax, polish or similar products cannot be overcoated.
- 2. It must be possible to overcoat the existing finish with Traffic.

Bona cannot guarantee good adhesion when overcoating finishes of another brand than Bona.

Traffic usually has very good adhesion to pre-finished floors but **the intercoat adhesion must always be checked** prior to overcoating: Prepare a small area as described below and apply a coat of Traffic. After 3 days scratch the floor surface gently with a coin. If the finish stays firmly attached to the surface the adhesion is satisfactory.

Preparation of factory pre-finished floors: Prior to application the floor must be treated with Bona Prep system according to the instructions on the Prep label.

Preparation of previously finished floors: Prior to application the floor must be treated with Bona Prep system according to the instructions on the Prep label using sanding disc/screen or sandpaper grade no. 150. Apply 1-2 coats of Traffic.

## Application

Ensure that the container is shaken thoroughly prior to use (or before decanting smaller quantities). Add 10% Traffic Hardener to the finish. Shake the mixture well immediately for at least 1 minute. The mixture of finish/hardener should be used within 5 hours when kept at 20°C. High temperature will reduce the pot life.

It is suggested that application is carried out using a Bona roller. Apply the finish evenly with a smooth flowing action avoiding accumulations of finish. **Note:** The room and finish temperature must not fall below +13°C during application and drying.

Application rate: 8-10 m<sup>2</sup>/litre (120-100g/m<sup>2</sup>) per coat.

Recommended primers: Prime Classic, Intense or Tempo, Gel



Recommended treatment schedules:

On bare wood:	1 x Prime + 2-3 x Traffic, 3 x Gel + 2-3 x Traffic or 3-4 x Traffic
Overcoating:	1-2 x Traffic

**Note:** For floors where there is a risk of sidebonding, e.g. endgrain floors, softwood plank floors and hardwood floors with underfloor heating, it is recommended that Prime Classic is used for the initial application.

After the first application a light sanding may be carried out using the Scrad system. For Traffic it is recommended that a sanding disc/screen or sandpaper grade no. 120 or finer is used.

Drying time: 3-4 hours per coat at 20°C/60% RH.

The floor will take light foot traffic approximately 8 hours after the final application. After approximately 1 week the finish will be completely cured. The floor can then be cleaned using a damp cloth and a neutral or slightly alkaline cleaning agent, e.g. Bona Parkett Cleaner, and carpets/rugs can be laid.

